1. A process for stabilizing a cyclotetrasiloxane against polymerization used in a chemical vapor deposition process for silicon oxides in electronic material fabrication, comprising; providing an effective amount of a free radical polymerization inhibitor to said cyclotetrasiloxane having the following formula:

5

10

15

20

$$R^7$$
 Si
 O
 Si
 R^3
 R^6
 O
 R^5

where R^{1-7} are individually selected from the group consisting of hydrogen, a normal, branched or cyclic C_{1-10} alkyl group, and a C_{1-4} alkoxy group.

The process of Claim 1 wherein said free radical scavenger is selected from the group consisting of: 2,6-ditert-butyl-4-methyl phenol, 2,2,6,6tetramethyl-1-piperidinyloxy, 2,6-dimethylphenol, 2-tert-butyl-4-hydroxyanisole, 3tert-butyl-4-hydroxyanisole, propyl ester 3,4,5-trihydroxy-benzoic acid, 2-(1,1dimethylethyl)-1,4-benzenediol, diphenylpicrylhydrazyl, 4-tert-butylcatechol, Nmethylaniline, 2,6-dimethylaniline, p-methoxydiphenylamine, diphenylamine. N,N'-diphenyl-p-phenylenediamine, p-hydroxydiphenylamine, phenol, octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate, tetrakis (methylene (3,5-di-tertbutyl)-4-hydroxy-hydrocinnamate) methane. phenothiazines, alkylamidonoisoureas. thiodiethylene bis (3,5,-di-tert-butyl-4-hydroxyhydrocinnamate, 1,2,-bis (3,5-di-tert-butyl-4-hydroxyhydrocinnamoyl) hydrazine, tris (2-methyl-4-hydroxy-5-tert-butylphenyl) butane, cyclic neopentanetetrayl bis (octadecyl phosphite), 4,4'-thiobis (6-tert-butyl-m-cresol), 2,2'-methylenebis (6tert-butyl-p-cresol), oxalyl bis (benzylidenehydrazide) and mixtures thereof.

- 3. The process of Claim 2 wherein said free radical scavenger is 2,6-ditert-butyl-4-methyl phenol.
- 4. The process of Claim 2 wherein said free radical scavenger is provided in an amount of 10-1000 ppm (wt.).
 - 5. The process of Claim 2 wherein said free radical scavenger is provided in an amount of of 50-500 ppm (wt.).
- 6. The process of Claim 2 wherein said free radical scavenger is provided in an amount of 50-250 ppm (wt.).

15

20

25

- 7. The process of Claim 2 wherein said free radical scavenger is provided in an amount of of 100-200 ppm (wt.).
- 8. A process for stabilizing 1,3,5,7-tetramethylcyclotetrasiloxane against polymerization used in a chemical vapor deposition process for silicon oxides in electronic material fabrication comprising providing an effective amount of a free radical scavenger polymerization inhibitor to said 1,3,5,7-tetramethylcyclotetrasiloxane.
- 9. The process of Claim 8 wherein said free radical scavenger is selected from the group consisting of 2,6-di-tert-butyl-4-methyl phenol, 2,2,6,6-tetramethyl-1-piperidinyloxy and mixtures thereof.
- 10. A process for stabilizing 1,3,5,7-tetramethylcyclotetrasiloxane against polymerization caused by oxygen, carbon dioxide and/or nitrogen trifluoride used in a chemical vapor deposition process for silicon oxides in electronic material fabrication comprising providing a free radical scavenger to said 1,3,5,7-tetramethylcyclotetrasiloxane.

- 11. The process of Claim 10 wherein said free radical scavenger is selected from the group consisting of 2,6-di-tert-butyl-4-methyl phenol, 2,2,6,6-tetramethyl-1-piperidinyloxy and mixtures thereof.
- 12. A composition of a cyclotetrasiloxane stabilizing against polymerization used in a chemical vapor deposition process for silicon oxides in electronic material fabrication, comprising; (a) said cyclotetrasiloxane having the following formula:

- where R¹⁻⁷ are individually selected from the group consisting of hydrogen, a normal, branched or cyclic C₁₋₁₀ alkyl group, and a C₁₋₄ alkoxy group, and (b) a free radical scavenger polymerization inhibitor.
- 13. A composition of 1,3,5,7-tetramethylcyclotetrasiloxane stabilized against polymerization used in a chemical vapor deposition process as a precursor for silicon oxides in electronic material fabrication comprising 1,3,5,7-tetramethylcyclotetrasiloxane and a free radical scavenger polymerization inhibitor.
- 14. A composition of 1,3,5,7-tetramethylcyclotetrasiloxane, used in a chemical vapor deposition process as a precursor for silicon oxides in electronic material fabrication, stabilized against polymerization, comprising (a) 1,3,5,7-tetramethylcyclotetrasiloxane, (b) a free radical scavenger selected from the group consisting of 2,6-di-tert-butyl-4-methyl phenol, 2,2,6,6-tetramethyl-1-

piperidinyloxy, 2-tert-butyl-4-hydroxyanisole, 3-tert-butyl-4-hydroxyanisole, propyl 3,4,5-trihydroxy-benzoic acid, 2-(1,1-dimethylethyl)-1,4-benzenediol, ester diphenylpicrylhydrazyl, 4-tert-butylcatechol, N-methylaniline, pmethoxydiphenylamine, diphenylamine, N,N'-diphenyl-p-phenylenediamine, phydroxydiphenylamine, phenol, octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl) propionate, tetrakis (methylene (3,5-di-tert-butyl)-4-hydroxy-hydrocinnamate) methane, phenothiazines, alkylamidonoisoureas, thiodiethylene bis (3,5,-di-tertbutyl-4-hydroxy-hydrocinnamate, 1,2,-bis (3,5-di-tert-butyl-4hydroxyhydrocinnamoyl) hydrazine, tris (2-methyl-4-hydroxy-5-tert-butylphenyl) butane, cyclic neopentanetetrayl bis (octadecyl phosphite), 4,4'-thiobis (6-tertbutyl-m-cresol), 2,2'-methylenebis (6-tert-butyl-p-cresol), oxalyl bis (benzylidenehydrazide) and mixtures thereof.

15

10

5

N:\DOCNOS\06223P USA.DOC

REFERENCES

- 1 User's Guide For: Glass Deposition with TEOS; Schumacher Group, Air Products and Chemicals, Inc., 1992.
- 5 2 Extrema® TOMCATS® (Tetramethylcyclotetrasiloxane) Product Data Sheet; Schumacher Group, Air Products and Chemicals, Inc., 2000.

10

25

- 3 Modeling of Low-Pressure Deposition of SiO₂ by Decomposition of TEOS; Schumacher Group, Air Products and Chemicals, Inc., 1979.
- 4 The Deposition of Silicon Dioxide Films at Reduced Pressure; Schumacher Group, Air Products and Chemicals, Inc., 6/1979.
- G. Lucovsky, Preparation of Device-quality SiO₂ Thin Films by Remote
 Plasma-enhanced Chemical Vapour Deposition (PECVD): Applications in
 Metal-Oxide-Semiconductor (MOS) Devices, Advanced Materials for
 Optics and Electronics, Vol. 6, 55-72 (1996).
- 6 G. Tochitani, M. Shimozuma and H. Tagashira, Deposition of silicon oxide films from TEOS by low frequency plasma chemical vapor deposition, *J. Vac. Sci. Technol. A*, Vol. 11, No. 2 Mar/Apr 1993.
 - 7 S. K. Ray, C. K. Maiti, S. K. Lahiri and N. B. Chakrabarti, Properties of silicon dioxide films deposited at low temperatures by microwave plasma enhanced decomposition of tetraethylorthosilicate, *J. Vac. Sci. Technol. B*, Vol. 10, No. 3, May/Jun 1992.
 - 8 C. S. Pai, J. F. Miner and P. D. Foo, Electron Cyclotron Resonance Microwave Discharge for Oxide Deposition Using Tetraethoxysilane, *J. Electrochem. Soc.*, Vol. 139, No. 3, March 1992.
 - 9 C.-P. Chang, C. S. Pai and J. J. Hsieh, Ion and chemical radical effects on the step coverage of plasma enhanced chemical vapor deposition of tetraethylorthosilicate films, *J. Appl. Phys.* 67 (4), 15 February 1990.
- 35
 10 C. S. Pai, J. F. Miner and P. D. Foo, Electron Cyclotron Resonance Microwave Discharge for Oxide Deposition Using Tetramethylcyclotetrasiloxane, *J. Appl. Phys.*, Vol. 73, No. 7, 1 April 1993.
- 40 11 A. Hochberg and B. Gelernt, User's Guide For: Undoped Glass, PSG, and BPSG Using TOMCATS® Source Material, Schumacher (Air Products and Chemicals, Inc.), 1991.
- 12 A. Lagendijk, Method of Forming Silicon Dioxide Glass Films, US Patent No. 5,028,566, 1991.

- 13 J. E. McGrath, J. S. Riffle, A. K. Banthia, I. Yilgor, I. and G. L Wilkes, An Overview of the Polymerization of Cyclosiloxanes, ACS Symp., Ser. 212 (Initiation Polym.), 145-72, 1983.
- 14 S. Hirabayashi and T. Nakamura, Silicone Rubber Compositions, U.S. Patent No. 5,548,006, 1996.
- M. A. Lutz, B. T. Nguyen and R. K. King, One Part Curable Compositions Containing Deactivated Hydrosilation Catalyst and Method for Preparing Same, U.S. Patent No. 5,380,812, 1995.

5

- 16 A. J. Chalk, Preparation of Stable Copolymerizable Organosilicon Compositions Containing a Platinum Catalyst and an Acrylonitrile Type Compound, U.S. Patent 3,344,111, 1967.
- 17 A. Berger and B. Bertolette Hardman, Latent Addition Curable Organopolysiloxane Compositions, U.S. Patent No. 3,882,083, 1975.
- 20 18 M. Endo and A. Yamamoto, Stabilization of Low-Molecular-Weight Methyl Cyclosiloxanes, Japanese Patent No. JP 07145179, 1999.